

ARECO ITALIA S.p.A.

Via Dell'Industria, 72/74 20083 VIGANO DI GAGGIANO (MI) Tel. (02) 90.85.372 - 90.86.270 Fax (02) 90.81.829

DATE: January 2010

TECHNICAL DATASHEET

PRODUCT: ZINC SPRAY PAINT

CODE: 70.0060/EcoDie

<u>PROPERTIES AND AREAS OF USE:</u> The content of zinc metal coating forms a highly corrosion resistant weathering. Protects tanks, pylons, joints welded bars, works of carpentry. Indicated after operations threading, cutting or welding to restore the corrosion resistance.

The 400 ml bottle covers an area of 1.5 - 2 meters, depending on the nature of support.

SUPPLY SPECIFICATIONS:

15 bar foil-coated can

Net content

Appearance

Colour

Scent

Density at 20℃

Pressure at 20℃

Pressure at 50℃

Flammability point

Viscosity Ford Cup 4

Remaining dry cylinder

Grit to grindometro

Gloss

Thickness 1 hand

Thickness 3 hands

Temperature resistance

Drying time:

Dust resistant

Dry to touch

Fully dry

May be painted over at any time

Childproof patented safety cap

Colour reference patch

400 ml

Can containing pressurised liquid

Miscellaneous

Typical solvent

0.75 - 0.80 g/ml

4.0 ± 0.5 bar

 $8.0 \pm 0.5 \text{ bar}$

less than 0°C

13"

From 20%

From 6 to 7 Micron

12 Gloss

7 Micron

36 Micron

120℃

10 minutes

20 minutes

24 hours

LABELLING:



HIGHLY INFLAMMABLE

Despite being considered reliable, this information is merely issued as a guideline. Its use implicates no liability by our company, including the breech of any patents or licenses. The user is responsible for checking that the product is suitable for the specific use.