

ARECO ITALIA S.p.A.

Via Dell'Industria, 72/74 20083 VIGANO DI GAGGIANO (MI) Tel. (02) 90.85.372 - 90.86.270 Fax (02) 90.81.829

DATE: January 2010

TECHNICAL DATASHEET

PRODUCT: BODYWORK RETOUCHING SPRAY PAINT

CODE: 91.000

PROPERTIES AND AREAS OF USE: Special fast-drying acrylic paint with high resistance to atmospheric agents. The quality of the substances used ensures the stability of the colours in time and repetition of the original colours, for retouching cars, motorbikes, scooters and bicycles. It withstands the effects of any fuel spillage.

High-gloss finishes are obtained, with good resistance to rubbing and polishing. The 400 ml can covers an area of 1.5 - 2 m², depending on the colour of the paint.

SUPPLY SPECIFICATIONS:

15 bar foil-coated can Net content Appearance Colour Scent Density at 20℃ Pressure at 20℃ Pressure at 50℃ Flammability point **Viscosity Ford Cup 4** Remaining dry cylinder Grit to grindometro Gloss Thickness 1 hand **Thickness 3 hands Temperature resistance** Drying time: **Dust resistant** Dry to touch Fully dry May be painted over at any time Childproof patented safety cap **Colour reference patch**

400 ml Can containing pressurised liquid Miscellaneous Typical solvent 0.75 - 0.80 g/ml 4.0 ± 0.5 bar 8.0 ± 0.5 bar less than 0°C From 11" to 11,5" From 12,4% to 17,2% From 0 to 2 Micron From 15 to 85 Gloss 7 - 10 Micron 20 - 30 Micron 100 - 130°C

10 minutes 20 minutes 24 hours

LABELLING:



IRRITANT



Despite being considered reliable, this information is merely issued as a guideline. Its use implicates no liability by our company, including the breech of any patents or licenses. The user is responsible for checking that the product is suitable for the specific use.