

**DATE: January 2010**

## **TECHNICAL DATASHEET**

**PRODUCT: MARINE ENGINE RETOUCHING SPRAY PAINT****CODE: 91.000/MM**

**PROPERTIES AND AREAS OF USE:** Special fast-drying acrylic paint with high resistance to atmospheric agents. The quality of the substances used ensures the stability of the colours in time and repetition of the original colours, for retouching marine engines, shafts and top cowlings. It withstands the effects of any fuel spillage.

High-gloss finishes are obtained, with good resistance to rubbing and polishing. Unsuitable for constant immersion.

The 400 ml can covers an area of 1.5 - 2 m<sup>2</sup>, depending on the colour of the paint.

### **SUPPLY SPECIFICATIONS:**

**15 bar foil-coated can****Net content****Appearance****Colour****Scent****Density at 20°C****Pressure at 20°C****Pressure at 50°C****Flammability point****Viscosity Ford Cup 4****Remaining dry cylinder****Grit to grindometro****Gloss****Thickness 1 hand****Thickness 3 hands****Temperature resistance****Drying time:****Dust resistant****Dry to touch****Fully dry****May be painted over at any time****Childproof patented safety cap****Colour reference patch****400 ml****Can containing pressurised liquid****Miscellaneous****Typical solvent****0.75 - 0.80 g/ml****4.0 ± 0.5 bar****8.0 ± 0.5 bar****less than 0°C****11,2"****From 12,4% to 17,2%****From 0 to 2 Micron****From 15 to 84 Gloss****7 – 10 Micron****20 – 30 Micron****110 – 130°C****10 minutes****20 minutes****24 hours**

### **LABELLING:**

**IRRITANT****HIGHLY  
INFLAMMABLE**

including the breach of any patents or licenses. The user is responsible for checking that the product is suitable for the specific use.