

**DATE: January 2010****TECHNICAL DATASHEET****PRODUCT: TROPICALISING SPRAY PAINT****CODE: 70.0040**

**PROPERTIES AND AREAS OF USE:** This protective paint combines the strength of galvanisation with attractive aesthetics. The quality and versatility of the applications remains unchanged, conveying resistance against corrosion to pylons, window bars and metal items in general.

The 400 ml can covers an area of 1.5 - 2 m<sup>2</sup>, depending on the type of element to be painted.

**SUPPLY SPECIFICATIONS:****15 bar foil-coated can****Net content****400 ml****Appearance****Can containing pressurised liquid****Colour****Tropicalised****Scent****Typical solvent****Density at 20°C****0.75 - 0.80 g/ml****Pressure at 20°C****4.0 ± 0.5 bar****Pressure at 50°C****8.0 ± 0.5 bar****Flammability point****less than 0° C****Viscosity Ford Cup 4****From 13'' to 15''****Remaining dry cylinder****18,80%****Grit to grindometro****From 4 to 6 Micron****Gloss****5 Gloss****Thickness 1 hand****12 Micron****Thickness 3 hands****38 Micron****Temperature resistance****100 – 120°C****Drying time:****Dust resistant****10 minutes****Dry to touch****20 minutes****Fully dry****24 hours****May be painted over at any time****Childproof patented safety cap****Colour reference patch****LABELLING:****HIGHLY  
INFLAMMABLE**

Despite being considered reliable, this information is merely issued as a guideline. Its use implicates no liability by our company, including the breach of any patents or licenses. The user is responsible for checking that the product is suitable for the specific use.