

## ARECO ITALIA S.p.A.

Via Dell'Industria, 72/74 20083 VIGANO DI GAGGIANO (MI) Tel. (02) 90.85.372 - 90.86.270 Fax (02) 90.81.829

**DATE: January 2010** 

CODE: 70.0070

## TECHNICAL DATASHEET

PRODUCT: DARK GALVANISING SPRAY PAINT

PROPERTIES AND AREAS OF USE: The high zinc content and special acrylic resins used lend the protective layer an effective barrier against atmospheric agents and salt. It can be used on pylons, pipes, tanks, metallic elements or welding joints to provide resistance to corrosion.

The 400 ml can covers an area of 1.5 - 2 m<sup>2</sup>, depending on the type of element to be painted.

## **SUPPLY SPECIFICATIONS:**

15 bar foil-coated can

**Net content** 400 ml

Can containing pressurised liquid **Appearance** 

Colour **Typical** 

**Scent Typical solvent** 0.75 - 0.80 g/ml Density at 20℃ Pressure at 20℃  $4.0 \pm 0.5 \, bar$ Pressure at 50℃  $8.0 \pm 0.5 \, bar$ Flammability point less than 0°C

**Viscosity Ford Cup 4** 13" Remaining dry cylinder 20,65% Percentage of zinc on the dry weight 20,1 %

From 6 to 7 Micron **Grit to grindometro** 

Gloss 9 Gloss Thickness 1 hand 12 Micron Thickness 3 hands 30 Micron

**Temperature resistance** 120℃ **Drying time: Dust resistant** 10 minutes

Fully dry May be painted over at any time Childproof patented safety cap

Colour reference patch

## **LABELLING:**

Dry to touch



**HIGHLY INFLAMMABLE** 



HARMFUL TO THE ENVIRONMENT

Despite being considered reliable, this information is merely issued as a guideline. Its use implicates no liability by our company, including the breech of any patents or licenses. The user is responsible for checking that the product is suitable for the specific use.

20 minutes

24 hours